

IGI Accumelt™ Waxes

IGI Accumelt™ Waxes have been chosen for use in cosmetic applications because of their narrow melting range. These waxes have been distilled to give exact phase change characteristics and molecular weight ranges. They can be used to enhance stability, control the melting point and the congealing/melting cycle time.

PHYSICAL PROPERTIES OF Accumelt 72 (R-3091A)

TEST METHODS	ASTM METHOD	SPECIFICATIONS*		TYPICAL
		Minimum	Maximum	
Congeaing Point °F (°C)	D 938	156.2 (69)	159.8 (71)	158 (70)
Peak Melt Point (DSC) °F (°C)		158 (70)	161.6 (72)	161.6 (72)
Kinematic Viscosity, cSt @ 212°F (100°C)	D 445	5.0	8.0	6.0
ASTM Color	D 6045	----	2.0	----
Needle Penetration, dmm @ 77°F (25°C)	D 1321	10	20	15
Needle Penetration, dmm @ 110°F (43.3°C)	D 1321	20	30	25

Note: Physical properties for which ONLY a typical value is listed are included as additional information but may not be printed on the COA.

INCI Name: Synthetic Wax

PRODUCT FORM AND PACKAGING:

Accumelt 72 (8719A) is offered as free flowing pellet, packed in 25kg bags stretch-wrapped onto 1000 kg pallets.

FDA STATUS:

Please contact an IGI representative for information concerning the FDA status of this product.

THE INTERNATIONAL GROUP INC.

USA

1100 East Main St.
Titusville
PA 16354

Toll Free: 1-800-852-6537
Telephone: (814) 827-4900

Canada

50 Salome Drive
Toronto
Ontario M1S 2A8

Toll Free: 1-800-561-3509
Telephone: (416) 293-4151

Visit our website at:

www.igiwax.com
www.igicares.com

NOTICE: All statements, information, and data given herein are believed to be accurate and reliable, but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

1/7/09



THE INTERNATIONAL GROUP, INC.