



IGI Microcrystalline Wax

IGI Microcrystalline Waxes have a wide variety of cosmetic applications. These waxes provide structure and binding properties while providing flexibility and softness for a wide range of products. They are used in a full range of color cosmetics.

PHYSICAL PROPERTIES OF MICROSERE 5909A

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Drop Melt Point °F (°C)	D 127	192 (88.9)	----	194 (90.0)
Kinematic Viscosity, cSt @ 212°F (100°C)	D 445	16.5	----	20.1
Oil Content, Wt%	D 721	----	1.8	0.5
ASTM Color	D 6045	----	0.5	0.2
Odor	D 1833	----	2	1
Needle Penetration, dmm @ 77°F (25°C)	D 1321	----	10	7

Note: Physical properties for which ONLY a typical value is listed are included as additional information but may not be printed on the COA.

INCI Name: Cera Microcristallina

FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710 for use in non-food articles in contact with food and in 21 CFR 172.886 for use in food.

THE INTERNATIONAL GROUP INC.

USA

1100 East Main St.
Titusville
PA 16354

Toll Free: 1-800-852-6537
Telephone: (814) 827-4900

Canada

50 Salome Drive
Toronto
Ontario M1S 2A8

Toll Free: 1-800-561-3509
Telephone: (416) 293-4151

Visit our website at:

www.igiwax.com
www.igicare.com

NOTICE: All statements, information, and data given herein are believed to be accurate and reliable, but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

